



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ :

C04B 35/01, 35/10, 35/12, 41/88 // 111:94

A1

(11) International Publication Number:

WO 00/40520

(43) International Publication Date:

13 July 2000 (13.07.00)

(21) International Application Number: PCT/AU99/01140

(22) International Filing Date: 23 December 1999 (23.12.99)

(30) Priority Data:

PP 7988

31 December 1998 (31.12.98) AU

(71) Applicant (for all designated States except US): CERAMIC FUEL CELLS LIMITED [AU/AU]; 170 Browns Road, Noble Park, VIC 3174 (AU).

(72) Inventor; and

(75) Inventor/Applicant (for US only): JAFFREY, Donald [AU/AU]; 2 Bonnieview Road, Mount Dandenong, VIC 3767 (AU).


(74) Agents: HUNTSMAN, Peter, H. et al.; Davies Collison Cave, 1 Little Collins Street, Melbourne, VIC 3000 (AU).

(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published

With international search report.

(54) Title: ELECTRICALLY CONDUCTIVE CERAMICS



(57) Abstract

A metal oxide ceramic material such as alumina or chromia which has been rendered electrically conductive through its thickness by the incorporation of silver into the material. The metal oxide ceramic material may be in the form of a layer on a substrate such as a bipolar plate or other component for a fuel cell assembly. The electrical conductivity may be achieved by heating the ceramic material and a silver-containing material in contact with each other to at least 750 °C such that silver migrates from the silver-containing material into the metal oxide ceramic material and creates electrically conductive pathways through the ceramic material. In a particular embodiment, the substrate is a steel which forms an alumina, chromia or alumina-rich or chromia-rich surface layer in oxidising atmosphere and the silver-containing material is heated in an oxidising atmosphere in contact with the steel to cause the surface layer to form on the steel and to cause silver from the silver-containing material to occur in and create the electrically conductive pathways through the layer. The silver-containing material may be commercially pure silver or other forms of silver.